

PHYSICAL TESTING REPORT



Royal Mosa

Mosa Architectural Ceramics Center
Ground Floor
Grant House
56 - 60 St John's Street
London
EC1M 4HG

LUCIDEON

insight creating advantage

FAO: Mr. Damian Hunter

Report of Tests on: 206 V 0600601

Your Reference: Mosa Terra Maestricht Mid Grey 60x60cm

Lucideon Reference: (171641)-20023

Date Reported: 29-Jun-2017

Order Number: BACS

Date Logged: 13-Apr-2017

Date(s) of Test(s): 20-Jun-2017 to 20-Jun-2017

Determination of Slip Resistance

BS 7976-2: 2002 + A1:2013 Pendulum Testers - Method of Operation

| No. | Dry (Horizontal) | Dry (Vertical) | Dry (Diagonal) | Wet (Horizontal) | Wet (Vertical) | Wet (Diagonal) |
|------|------------------|----------------|----------------|------------------|----------------|----------------|
| 1 | 62 | 63 | 63 | 47 | 48 | 47 |
| 2 | 62 | 63 | 62 | 47 | 48 | 48 |
| 3 | 61 | 62 | 62 | 48 | 48 | 48 |
| 4 | 62 | 62 | 61 | 48 | 48 | 47 |
| 5 | 62 | 62 | 61 | 47 | 48 | 47 |
| Mean | 62 | 62 | 62 | 48 | 48 | 47 |

| Result: | Unit | 1 | 2 | 3 | 4 |
|----------|------|------|------|------|------|
| Ra Value | µm | 2.29 | 1.58 | 1.57 | 1.68 |
| Rz Value | µm | 12.6 | 10.6 | 10.2 | 11.3 |

Description of Test Specimen(s): 1 tile (tested with slider 96)

Average of 15 Dry Values: 62

Average of 15 Wet Values: 47

Temperature: 25 °C

The energy absorbed by contact with the pre-set distance is read from a physical scale by a pointer that follows the overswing of the pendulum arm. 12 results are averaged to give the final pendulum number which is used to categorise the tile surface. The UK Slip Resistance Group recommends the following guidelines, PTV 0-24 High Slip Potential, PTV 25-35 Moderate Slip Potential, PTV 36+ Low Slip Potential.

Opinions and interpretations expressed herein are outside the scope of UKAS Accreditation.

End of Test Report

Miss Zoe Kinally
Manager

This report is issued in accordance with the Conditions of Business of Lucideon Limited and relates only to the sample(s) tested. No responsibility is taken for the accuracy of the sampling unless this is done under our own supervision. This report shall not be reproduced in part without the written approval of Lucideon Limited, nor used in any way as to lead to misrepresentation of the results or their implications.

Lucideon is the trading name of Lucideon Limited. Registered in England No. 1960455.

Lucideon Limited
Queens Road, Penkhull
Stoke-on-Trent
Staffordshire ST4 7LQ

T +44 (0)1782 764428
enquiries@lucideon.com
www.lucideon.com

Page 1 of 1