

# PHYSICAL TESTING REPORT



## Royal Mosa

Mosa Architectural Ceramics Center  
Ground Floor  
Grant House  
56 - 60 St John's Street  
London  
EC1M 4HG

# LUCIDEON

insight creating advantage

FAO: Mr. Damian Hunter

**Report of Tests on:** 216 V 0600601

**Your Reference:** Mosa Terra Maestricht Anthracite 60x60cm

**Lucideon Reference:** (171641)-20022

**Date Reported:** 29-Jun-2017

**Order Number:** BACS

**Date Logged:** 13-Apr-2017

**Date(s) of Test(s):** 20-Jun-2017 to 20-Jun-2017

### Determination of Slip Resistance

BS 7976-2: 2002 + A1:2013 Pendulum Testers - Method of Operation

No.	Dry (Horizontal)	Dry (Vertical)	Dry (Diagonal)	Wet (Horizontal)	Wet (Vertical)	Wet (Diagonal)
1	62	62	63	44	44	42
2	63	61	62	44	44	42
3	62	61	62	43	44	42
4	61	61	62	43	44	43
5	62	61	61	43	43	42
Mean	62	61	62	43	44	42

Result:	Unit	1	2	3	4
Ra Value	µm	1.81	1.51	1.78	1.73
Rz Value	µm	10.9	11.2	12.2	12.4

Description of Test Specimen(s): 1 tile (tested with slider 96)

Average of 15 Dry Values: 62

Average of 15 Wet Values: 43

Temperature: 25 °C

The energy absorbed by contact with the pre-set distance is read from a physical scale by a pointer that follows the overswing of the pendulum arm. 12 results are averaged to give the final pendulum number which is used to categorise the tile surface. The UK Slip Resistance Group recommends the following guidelines, PTV 0-24 High Slip Potential, PTV 25-35 Moderate Slip Potential, PTV 36+ Low Slip Potential.

Opinions and interpretations expressed herein are outside the scope of UKAS Accreditation.

### End of Test Report

Miss Zoe Kinally  
Manager

This report is issued in accordance with the Conditions of Business of Lucideon Limited and relates only to the sample(s) tested. No responsibility is taken for the accuracy of the sampling unless this is done under our own supervision. This report shall not be reproduced in part without the written approval of Lucideon Limited, nor used in any way as to lead to misrepresentation of the results or their implications.

Lucideon is the trading name of Lucideon Limited. Registered in England No. 1960455.

Lucideon Limited  
Queens Road, Penkhull  
Stoke-on-Trent  
Staffordshire ST4 7LQ

T +44 (0)1782 764428  
enquiries@lucideon.com  
www.lucideon.com

Page 1 of 1